



Mirafi® BXG10

Mirafi® BXG10 geogrid is composed of high molecular weight, high tenacity polyester multifilament yarns which are woven in tension and finished with a PVC coating. Mirafi® BXG10 geogrid is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Tensile Strength (at ultimate)	ASTM D 6637	kN/m (lbs/ft)	12.4 (850)	19.0 (1300)
Tensile Strength (at 2% strain)	ASTM D 6637	kN/m (lbs/ft)	4.1 (280)	6.6 (450)
Tensile Strength (at 5% strain)	ASTM D 6637	kN/m (lbs/ft)	8.5 (580)	13.4 (920)
UV Resistance (at 500 hours)	ASTM D 4355	% strength retained	70	

Physical Properties	Test Method	Unit	Typical Value
Percent Open Area	COE CW-02215	%	70
Grid Aperture Size (MD)	--	mm (in)	25.4 (1.0)
Grid Aperture Size (CMD)	--	mm (in)	25.4 (1.0)
Mass/Unit Area	ASTM D 5261	g/m ² (oz/yd ²)	278 (8.2)
Roll Dimensions (width x length)	--	m (ft)	4 (13.1) x 69 (225)
Roll Area	--	m ² (yd ²)	274 (328)
Estimated Roll Weight	---	kg (lbs)	82 (182)

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2010 TenCate Geosynthetics North America
Mirafi® is a registered trademark of Nicolon Corporation

